

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C07C 7/20, 15/46</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 96/16921</b> <b>(43) International Publication Date:</b> 6 June 1996 (06.06.96)
<b>(21) International Application Number:</b> PCT/EP95/04501 <b>(22) International Filing Date:</b> 16 November 1995 (16.11.95)  <b>(30) Priority Data:</b> 08/345,097 28 November 1994 (28.11.94) US 08/383,279 3 February 1995 (03.02.95) US  <b>(71) Applicant:</b> CIBA-GEIGY AG [CH/CH]; Klybeckstrasse 141, CH-4002 Basle (CH).  <b>(72) Inventors:</b> WINTER, Roland, Arthur, Edwin; 23 Banksville Road, Armonk, NY 10504 (US). VON AHN, Volker, Hartmut; 30 Greenfield Road, Mahopac, NY 10541 (US).		<b>(81) Designated States:</b> AL, AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, IS, JP, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, TJ, TM, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, LS, MW, SD, SZ, UG).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> A METHOD FOR INHIBITING PREMATURE POLYMERIZATION OF VINYL AROMATIC MONOMERS  <b>(57) Abstract</b> <p>Nitroxyl inhibitors in combination with some oxygen reduce the premature polymerization of vinyl aromatic monomers during the manufacturing processes for such monomers. Even small quantities of air used in combination with the nitroxyl inhibitors result in vastly prolonged inhibition times for said monomers.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

A METHOD FOR INHIBITING PREMATURE POLYMERIZATION  
OF VINYL AROMATIC MONOMERS

This invention pertains to the compositions, processes and methods of using nitroxyl inhibitors in combination with oxygen, to prevent the premature polymerization of vinyl aromatic monomers.

It is well known that vinyl aromatic monomer compounds such as styrene or  $\alpha$ -methylstyrene, have a strong tendency to polymerize when subjected to elevated temperatures. Manufacturing processes for such monomers typically include distillations at elevated temperatures.

To prevent premature polymerization of vinyl aromatic monomers during the distillation purification process, various compounds have been disclosed as polymerization inhibitors. These include elemental sulfur and many classes of organic chemicals. These materials have met with varying degrees of success in industrial use. Included among these organic materials are nitrated phenol derivatives, C- and N-nitroso compounds and nitroxyl derivatives. A particularly effective class of such inhibitors are hindered amine nitroxyls. This class of stable free radicals is characterized by having a  $\text{NO}^*$  group, where the \* asterisk denotes an unpaired electron, and where the nitrogen atom is further flanked by two carbon atoms, to neither of which hydrogen atoms are attached. Often these flanking carbon atoms are further connected by various bridging groups to form cyclic structures, such as, for example, six-membered piperidines, piperazines, five membered pyrrolidines and the like. Collectively these stable free nitroxyl radicals (also called nitroxides) are referred to as "hindered amine" nitroxyl free radicals. Compounds of this class are not only valuable inhibitors of free radical-initiated polymerization in unsaturated monomers, but also have found uses as spin labels in biochemical applications.

Soviet Patent No. 1,027,150 discloses the stabilization of styrene by using nitroxyl radical. Soviet Patent No. 1,139,722 discloses the use of a bis-nitroxyl radical as the thermal polymerization inhibitor for styrene. Japanese Hei 1-165534 discloses the use of

1-piperidyloxy derivatives as polymerization inhibitors for styrene. Soviet Patent No. 1,558,888 discloses the polymerization inhibition of styrene by a nitroxyl radical. U.S. Patent No. 3,733,326 discloses the polymerization inhibition of vinyl monomers by free radical precursors. The inhibition of styrene polymerization by some hindered amine nitroxyl derivatives is also discussed by Y. Miura, S. Masuda, and M. Kinoshita, *Die Makromolekulare Chemie*, **1972**, 160, 243-249, M.D. Gold'fein, E.A. Ragikov, V.N. Kozhevnikov, A.D. Stepukhovich and A.V. Trubnikov, *Vysokomol. soyed.* **1975**, A17 (8), 1671-1677 translated in *Polymer Science (USSR)*, **1975**, A17(8), 1919-1927 and by G. Moad, E. Rizzardo, and D.H. Solomon, *Polymer Bulletin* **1982**, 6, 589-593. Inhibition of polymerization of vinyl aromatic compounds by a combination of a stable nitroxyl compound with aromatic nitro compounds is the subject of U.S. Patent No. 5,254,760 (1993).

One object of the present invention is to provide a composition comprising a vinyl aromatic compound, and an effective amount of nitroxyl inhibitor and oxygen or air to optimize the effectiveness of the inhibitor.

Another object of the invention is to provide a process for the highly efficient utilization of nitroxyl inhibitors.

It is now been found that the effectiveness of nitroxyl inhibitors in vinyl aromatic monomers can be boosted substantially by the concomitant presence of small quantities of oxygen or air. The inhibition time, i.e the time to the onset of polymerization, is thus typically increased two- to four-fold, compared to completely oxygen free conditions. In some cases the continuous or intermittent addition of air throughout a distillation run may not be desirable where oxygen-free conditions are preferred as standard operating mode. In such cases, the insertion of air into the system can still be employed to quench instantly any polymerization that may have started during upset conditions, thus to avert any disastrous runaway polymerizations from occurring.

The method of boosting inhibiting activity with air or oxygen is particularly noteworthy and unobvious in view of existing literature indicating that oxygen does catalyze rather than inhibit thermal styrene polymerization (P.D. Bartlett, *Angew.Chem.*, **67**, 45-52 (1955), even though oxygen is known to inhibit the polymerization of other monomers such as acrylic monomers.

The instant invention pertains to a composition which comprises

- (a) a vinyl aromatic compound, and
- (b) an effective inhibiting amount, sufficient to prevent premature polymerization during distillation or purification of said vinyl aromatic compound, of a stable hindered nitroxyl compound used together with an effective amount of oxygen or air to enhance the inhibiting activity of the nitroxyl compound.

The effective amount of nitroxyl compound is, for example, from 1 to 2000 ppm, based on the weight of component (a).

Preferably the amount of nitroxyl compound is from 5 to 1000 ppm, based on the weight of component (a).

The effective amount of oxygen or air is, for example, 10 ppm to about 1000 ppm, based on the weight of component (a). The upper practical limit for this amount will be determined by safety considerations.


The vinyl aromatic monomer of component (a) is, for example, selected from the group consisting of styrene,  $\alpha$ -methylstyrene, vinyltoluene, divinylbenzene, styrenesulfonic acid and structural isomers, derivatives of said compounds and mixtures thereof.

Preferably, the vinyl aromatic monomer is styrene,  $\alpha$ -methylstyrene, vinyltoluene or divinylbenzene; most preferably styrene.

This invention is applicable to hindered amine nitroxyl radicals in general, i.e. compounds having at least one NO\* group, where the \* asterisk denotes an unpaired electron, and the nitrogen atom is further flanked by two carbon atoms, to neither of which hydrogen atoms are attached. These flanking carbon atoms may be further connected by various bridging groups to form cyclic structures such as for example six-membered piperidines, piperazines, five membered pyrrolidines and the like.

The hindered amine nitroxyl compounds useful in this invention may, for example, correspond to the generic structure


- 4 -



where

each R is alkyl and T is a group required to complete a 5- or 6-membered ring.

Two or more nitroxyl groups may be present in the same molecule by being linked through the T moiety as exemplified below where E is a linking group.



Further hindered amine nitroxyl compounds are those of formulae I to III, in particular formula II, disclosed on page 3 of EP-A-592 363 wherein the hindered N atom bears an -O\* radical; as well as those of general formulae IV to X on pages 4 to 21 of EP-A-592363 wherein G<sup>11</sup> is oxyl.

Non-limiting examples for nitroxyl compounds useful in the present invention are listed below:

- di-tert-butyl nitroxyl,
- 1-oxyl-2,2,6,6-tetramethylpiperidine,
- 1-oxyl-2,2,6,6-tetramethylpiperidin-4-ol,
- 1-oxyl-2,2,6,6-tetramethylpiperidin-4-one,
- 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl acetate,
- 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl propionate,
- 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl 2-ethylhexanoate,

1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl stearate,  
1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl benzoate,  
1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl 4-tert-butylbenzoate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) succinate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) adipate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) sebacate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) n-butylmalonate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) phthalate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) isophthalate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) terephthalate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) hexahydroterephthalate,  
N,N'-bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)adipamide,  
N-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)caprolactam,  
N-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)dodecylsuccinimide,  
2,4,6-tris-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) cyanurate,  
2,4,6-tris-[N-butyl-N-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)]-s-triazine, or  
4,4'-ethylenebis(1-oxyl-2,2,6,6-tetramethylpiperazin-3-one).

Preferably, the hindered amine nitroxyl compound of component (b) is

bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) sebacate,  
1-oxyl-2,2,6,6-tetramethylpiperidine,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) n-butylmalonate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) succinate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) hexahydroterephthalate,  
1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl 4-tert-butylbenzoate,  
1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl propionate, or  
1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl benzoate.

It is also within the purview of the instant invention that the composition may also contain a solvent such as ethylbenzene or contain dissolved polymer such a saturated or unsaturated polyester.

The instant invention also pertains to a process for inhibiting the premature polymerization of a vinyl aromatic compound during distillation or purification which comprises incorporating therein an effective inhibiting amount, sufficient to prevent premature polymerization during distillation or purification of said vinyl aromatic compound, of a stable hindered nitroxyl

compound used together with an effective amount of oxygen or air to enhance the inhibiting activity of the nitroxyl compound.

The vinyl aromatic compound is distilled or purified at a temperature from 50°C to 150°C. The stable nitroxyl compound is added to the vinyl aromatic compound continuously or intermittently upstream to the point where distillation or purification occurs; or the stable nitroxyl compound can be added at different entry points into the vinyl aromatic compound process stream prior to the point where distillation or purification occurs.

The instant process can be started under either anaerobic or aerobic conditions with air or oxygen then being added continuously or intermittently thereafter to the vinyl aromatic monomer to prolong polymerization inhibition time or to short-stop incipient polymerization.

The term vinyl aromatic monomer includes any of readily polymerizable vinyl aromatic compounds, e.g. styrene,  $\alpha$ -methylstyrene, vinyltoluene, divinylbenzene, styrenesulfonic acid and structural isomers, and derivatives and mixtures thereof. The preferred compounds and amounts for carrying out the inventive process are as given for the aforementioned inventive composition.

The effective amount of polymerization inhibitors added may vary over wide ranges depending upon the particular vinyl aromatic compound and the conditions of distillation. Preferably, the total amount of a nitroxyl compound is from 1 ppm to about 2,000 ppm based upon the weight of the monomer being inhibited. For most applications, the inhibitor system is used in the range of 5 to 1,000 ppm. As the temperature increases, greater amounts of inhibitor are required. During distillation of the vinyl aromatic mixtures, the temperature of the reboiler is, generally, in the range of 50°C to about 150°C. The polymerization inhibitor can be introduced into the monomer to be protected by any conventional method. It may be added as a concentrate solution in suitable solvents just upstream of the point of desired application by any suitable means. Since the inhibitor is gradually depleted during operation, it is generally necessary to maintain the appropriate amount of the inhibitor in the distillation apparatus by adding inhibitor during the course of the distillation process. Such addition may be carried out either on a generally continuous basis or it may consist of intermittently charging inhibitor into the distillation system when the concentration of inhibitor is to be maintained above the minimum required level.

The instant invention also pertains to the use of a stable hindered nitroxyl compound together with an effective amount of oxygen or air to enhance the inhibiting activity of the nitroxyl compound for inhibiting the premature polymerization of a vinyl aromatic compound during distillation or purification. The preferred compounds and amounts are as given for the aforementioned inventive composition.

The examples below illustrate the invention in a series of batch experiments. It is obvious to those skilled in the art that the invention is equally applicable to continuous processes and steady state conditions, typical of industrial manufacturing processes for vinyl aromatic monomers.

The following examples will serve to further illustrate the invention. In the examples, styrene, which is representative of vinyl aromatic monomers, is used as the test monomer.

#### Examples 1-5

Commercial grade styrene is freed of tert-butyl catechol storage stabilizer by washing with 1 N sodium hydroxide solution, water and subsequent distillation under reduced pressure. A 300 mL 3-necked flask equipped with thermometer, condenser, rubber septum and magnetic stirrer bar is charged with 100 g of styrene, purified as described above, and 50 mg of bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) sebacate, to give a 500 ppm solution of this representative nitroxyl inhibitor.

An oxygen-free atmosphere is established by five consecutive evacuations and backfilling with nitrogen, followed by sparging the styrene solution with pure nitrogen for 15 minutes. The vessel is immersed into a mechanically stirred and thermostatically controlled oil bath at 120°C. Samples are withdrawn at twenty minute intervals, and the amount of polystyrene formed is then determined by refractive index measurements which in turn are calibrated with authentic polystyrene in styrene solutions of known concentration. The onset of polymerization occurs abruptly at the end of a characteristic induction period. The length of this induction period the "inhibition time" is determined experimentally by extrapolating the linear polymer/time curve.

Under anaerobic condition the inhibition time is 50 minutes. Under a static air atmosphere the inhibition time almost tripled to 147 minutes. It is further demonstrated that even minute quantities of air bring about vastly enhanced inhibition times. Thus, air is sparged

continuously at 0.4 mL/min into a previously rigorously anaerobic system. Sparging is started when the vessel is immersed into a preheated oil bath. The resulting inhibition time is 188 minutes.

In Examples 4-5, no inhibitor is added to the system whether done under nitrogen or under air. The polymerization onset occurs after only 6 minutes in each instance, which is the time period required to heat the reaction mass from room temperature to 120°C.

The results of these experiments are shown in the table below.

<u>Example</u>	<u>1-Oxyl Inhibitor (ppm)</u>	<u>Initial Atmosphere</u>	<u>Sparge Rate mL/min</u>	<u>Inhibition Time (min)</u>
1(Comp.)	500	nitrogen	none	50
2	500	air(static)	none	147
3	500	nitrogen	0.4	188
4(Comp.)	none	nitrogen	none	6
5(Comp.)	none	air(static)	none	6

The six minute delay in the start of polymerization [Comparative Examples 4 and 5; 4(Comp.) and 5(Comp.)] largely reflects the time needed to heat the samples from 25°C to 120°C. These examples demonstrate that with the vinyl aromatic monomers such as styrene, unlike other unsaturated monomers such as acrylic acid, oxygen alone is not an effective polymerization inhibitor.

#### Examples 6-8

The addition of air is also used as a short-stop of polymerization once polymerization has started under anaerobic conditions. Thus, the experiment of Example 1 is repeated under strictly anaerobic conditions. At the end of the normal inhibition time of ca. 50 minutes, polymerization starts and is allowed to proceed for ten minutes. This results in a styrene polymer content of 1%. At that point a single addition of 50 mL of air is injected into the solution at a rate of 6 mL/min. This air quantity contains 10.5 ml (0.43 mmoles) or 14 mg of oxygen which amounts to 140 ppm of oxygen relative to styrene. As a result the polymerization ceases instantaneously and onset of further polymerization is delayed by an additional 65 minutes.

Even longer delay times are achieved by the injection of higher air volumes. Thus, 500 ml of air, delivered over 10 minutes at 50 mL/minute produced 98 additional minutes of inhibition time. Continuous air sparging at 50 mL/min resulted in 135 minutes additional delay before polymerization onset. Controlled sparging with air thus represents a means not only to boost the efficiency of nitroxyl inhibitors, but also to quench incipient polymerization instantaneously once it starts.

These results are summarized in the table below.

<u>Example</u>	1-Oxyl Inhibitor (ppm)	Initial Atmosphere	Volume Air Added	Inhibition Time (min)
			<u>mL</u>	
1	500	nitrogen	none	50
6	500	nitrogen	50	50 + 65
7	500	nitrogen	500	50 + 98
8	500	nitrogen	7000	50 + 135

#### Comparative Example 9

Following the procedure of Example 1 under strictly anaerobic conditions, 541 ppm of 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl benzoate in styrene is heated at 120°C and produces the same inhibition time of 50 minutes as the difunctional inhibitor of Example 1. The molar nitroxyl concentration of this monofunctional derivative is the same as the molar nitroxyl group concentration of the difunctional derivative of Example 1.

#### Example 10

Under an air atmosphere and additional continuous air sparging at a rate of 2 mL/min, 100 g of styrene is heated at 120°C in presence of 500 ppm of 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl benzoate. Polymerization onset is only seen after 190 minutes of total inhibition time. In this case the air addition results in a fourfold increase in inhibitor effectiveness compared to the same inhibitor used in comparative Example 9, but without the addition of air to the system.

#### Examples 11-16

To ascertain the performance of a variety of other hindered amine nitroxyl derivatives under aerobic and anaerobic conditions, samples of styrene solutions containing 500 ppm

of various nitroxyl inhibitors are heated in sealed vials in a forced draft oven at 120°C vials under air as well as under nitrogen atmospheres. The onset of polymerization is again determined from sudden shifts of refractive index. Inhibition times under air and nitrogen are tabulated below.

<u>Example*</u>	<u>Inhibition Time (minutes)</u>	
	<u>Nitrogen</u>	<u>Air</u>
11	98	210
12	70	146
13	72	147
14	75	134
15	73	142
16	79	140

\*11 - 1-oxyl-2,2,6,6-tetramethylpiperidine

12 - bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) n-butylmalonate

13 - bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) succinate

14 - bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) hexahydroterephthalate

15 - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl 4-tert-butylbenzoate

16 - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl propionate

These results clearly show that the instant nitroxyl compounds generally are very effective inhibitors for vinyl aromatic monomers such as styrene, and that their effectiveness as inhibitors can be greatly enhanced by the concomitant presence of oxygen as seen by the prolonged inhibition times when air is present.

## WHAT IS CLAIMED IS:

1. A composition which comprises
  - (a) a vinyl aromatic compound, and
  - (b) an effective inhibiting amount, sufficient to prevent premature polymerization during distillation or purification of said vinyl aromatic compound, of a stable hindered nitroxyl compound used together with an effective amount of oxygen or air to enhance the inhibiting activity of the nitroxyl compound.
2. A composition according to claim 1 wherein the effective amount of nitroxyl compound is from 1 to 2000 ppm, based on the weight of component (a).
3. A composition according to claim 2 wherein the amount of nitroxyl compound is from 5 to 1000 ppm, based on the weight of component (a).
4. A composition according to claim 1 wherein the effective amount of oxygen or air is 10 ppm to about 1000 ppm, based on the weight of component (a).
5. A composition according to claim 1 wherein the vinyl aromatic compound of component (a) is selected from the group consisting of styrene,  $\alpha$ -methylstyrene, vinyltoluene, divinylbenzene, styrenesulfonic acid and structural isomers, derivatives of said compounds and mixtures thereof.
6. A composition according to claim 1 wherein the vinyl aromatic compound is styrene,  $\alpha$ -methylstyrene, vinyltoluene or divinylbenzene.
7. A composition according to claim 1 wherein the stable hindered nitroxyl compound of component (b) is selected from the group consisting of
  - di-tert-butyl nitroxyl,
  - 1-oxyl-2,2,6,6-tetramethylpiperidine,
  - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-ol,
  - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-one,
  - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl acetate,
  - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl propionate,
  - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl 2-ethylhexanoate,
  - 1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl stearate,

1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl benzoate,  
1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl 4-tert-butylbenzoate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) succinate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) adipate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) sebacate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) n-butylmalonate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) phthalate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) isophthalate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) terephthalate,  
bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) hexahydroterephthalate,  
N,N'-bis(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)adipamide,  
N-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)-caprolactam,  
N-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)-dodecylsuccinimide,  
2,4,6-tris(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl) isocyanurate,  
2,4,6-tris-[N-butyl-N-(1-oxyl-2,2,6,6-tetramethylpiperidin-4-yl)]-s-triazine, and  
4,4'-ethylenebis(1-oxyl-2,2,6,6-tetramethylpiperazin-3-one).

8. A composition according to claim 1 which additionally contains a solvent or dissolved polymer.
9. A composition according to claim 8 wherein the solvent is ethylbenzene or the dissolved polymer is a saturated or unsaturated polyester.
10. A process for inhibiting the premature polymerization of a vinyl aromatic compound during distillation or purification which comprises incorporating therein an effective inhibiting amount, sufficient to prevent premature polymerization during distillation or purification of said vinyl aromatic compound, of a stable hindered nitroxyl compound used together with an effective amount of oxygen or air to enhance the inhibiting activity of the nitroxyl compound.
11. A process according to claim 10 wherein the vinyl aromatic compound is distilled or purified at a temperature from 50°C to 150°C.
12. A process according to claim 10 wherein the stable nitroxyl compound is added to the vinyl aromatic compound continuously or intermittently upstream to the point where distillation or purification occurs.

13. A process according to claim 10 wherein the stable nitroxyl compound is added at different entry points into the vinyl aromatic compound process stream prior to the point where distillation or purification occurs.

14. A process according to claim 10 wherein the amount of stable nitroxyl compound is from 1 to 2000 ppm, based on the weight of vinyl aromatic compound.

15. A process according to claim 10 which is started under anaerobic conditions where oxygen or air are continuously or intermittently added thereafter.

16. A process according to claim 10 which is carried out under aerobic conditions.

17. A process according to claim 10 where air or oxygen is added intermittently to the vinyl aromatic compound to prolong polymerization inhibition time or to short-stop incipient polymerization.

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 95/04501

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C07C7/20 C07C15/46		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C07C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,3 988 212 (WATSON JAMES M) 26 October 1976 see example 1 ---	10-17
X	US,A,4 466 904 (WATSON JAMES M ET AL) 21 August 1984 see the whole document ---	10-17
X	US,A,4 468 343 (BUTLER JAMES R ET AL) 28 August 1984 see the whole document ---	10-17
A	EP,A,0 581 737 (CIBA GEIGY AG) 2 February 1994 ---	1-9
A	GB,A,1 218 456 (BP CHEMICALS) 6 January 1971 ---	1-9
-/-		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the international search  23 February 1996		Date of mailing of the international search report  25.03.96
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+ 31-70) 340-3016		Authorized officer  Janus, S

Form PCT/ISA/210 (second sheet) (July 1992)

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 95/04501

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO,A,95 03263 (UNIROYAL CHEM CO INC ;KOURBATOV VLADIMIR ANATOLIEVIC (RU); BOREYKO) 2 February 1995 see the whole document -----	1-17

## INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.

PCT/EP 95/04501

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-3988212	26-10-76	DE-A- 2611142	14-10-76
		FR-A- 2304595	15-10-76
		GB-A- 1490052	26-10-77
		JP-A- 51115428	12-10-76
		NL-A- 7602141	23-09-76
-----			
US-A-4466904	21-08-84	NONE	
-----			
US-A-4468343	28-08-84	CA-A- 1224811	28-07-87
		DE-A- 3413642	11-10-84
		FR-A,B 2543944	12-10-84
		GB-A,B 2138010	17-10-84
		JP-B- 6080085	12-10-94
		JP-A- 59206419	22-11-84
-----			
EP-A-0581737	02-02-94	US-A- 5254760	19-10-93
		AU-B- 4425093	03-02-94
		CA-A- 2101359	30-01-94
		CN-A- 1084155	23-03-94
		JP-A- 6166636	14-06-94
-----			
GB-A-1218456	06-01-71	DE-A- 1944233	09-04-70
		FR-A- 2017512	22-05-70
-----			
WO-A-9503263	02-02-95	AU-B- 7237094	20-02-95
-----			